

3M™ Sun Control Window Film


Ceramic Architectural CA80



Heat rejection with high clarity and enhanced views

Benefits

- ▶ High visible light transmission providing excellent aesthetics
- ▶ Low interior and exterior reflectivity enhances views while maintaining exterior appearance
- ▶ Stay cooler by reducing excessive heat in warmer months
- ▶ Non-metalized film with natural tone for amazing clarity
- ▶ Helps extend the life of furnishings by significantly reducing harmful UV rays, the largest cause of fading
- ▶ Comprehensive warranty from 3M



© 3M 2024. All rights reserved. 3M is a trademark of 3M. Used under license in Canada. All other trademarks are property of their respective owners. Please recycle. 75-5100-2955-8

3M Commercial Branding and Transportation Division
3M Center, Building 223-3N-30
St. Paul, MN 55144-1000
3M.com/windowfilm



Warranty and Limited Remedy: 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER EXPRESS OR IMPLIED WARRANTIES OR CONDITIONS, INCLUDING ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If the 3M product does not conform to this warranty, the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price. Limitation of Liability: Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted.

LEED Certification

Window films may be used toward the following LEED credits:

◀ EA-1	◀ EQ-7.1	◀ MR 5.1-5.2	◀ EQ-8.1-8.2
◀ SS-8	◀ EQ-7.1	◀ EQ-7.2	◀ ID

Product Performance and Technical Data

Glass Type (All 1/4")	Visible Light Transmittance (VLT)	Visible Light Reflection (Interior)	Visible Light Reflection (Exterior)	Visible Light Transmittance	Total Solar Energy Rejected	Solar Heat Gain Coefficient (G Value)	U Value btu/ht ² F	U Value w/m ² K	Solar Heat Rejection	UV Light Rejection	Glare Reduction	Visible Light to Solar Heat Gain Ratio
Clear	8%	8%	8%	77%	43%	0.57	1.06	5.9	30%	99.6%	13%	1.4
Tinted	6%	6%	6%	46%	52%	0.48	1.06	5.9	25%	99.8%	13%	1.0
Double Clear	13%	15%	15%	69%	39%	0.62	0.48	2.7	13%	99.7%	13%	1.1
Double Tinted	12%	8%	41%	55%	55%	0.45	0.48	2.7	11%	99.8%	13%	0.9